



US006379962B1

(12) **United States Patent**  
**Holy et al.**

(10) **Patent No.:** **US 6,379,962 B1**  
(45) **Date of Patent:** **Apr. 30, 2002**

(54) **POLYMER SCAFFOLD HAVING  
MICROPOROUS POLYMER STRUTS  
DEFINING INTERCONNECTED  
MACROPORES**

(75) Inventors: **Chantal E. Holy; Molly S. Shoichet;  
John E. Davies**, all of Toronto (CA)

(73) Assignee: **Bonetec Corporation**, Toronto (CA)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **09/191,107**

(22) Filed: **Nov. 13, 1998**

(30) **Foreign Application Priority Data**

Nov. 14, 1997 (CA) ..... 2221195

(51) **Int. Cl.**<sup>7</sup> ..... **C12N 5/06**; C12N 5/08;  
C12N 11/08; A61F 2/00

(52) **U.S. Cl.** ..... **435/395**; 424/39.7; 424/423;  
435/180; 435/396; 435/402

(58) **Field of Search** ..... 424/93.7, 423;  
435/174, 180, 182, 395, 396, 402

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

5,041,138 A	8/1991	Vacanti et al.	623/16
5,228,994 A *	7/1993	Tkacik et al.	210/500.29
5,338,772 A	8/1994	Bauer et al.	523/115
5,498,335 A *	3/1996	Moya	210/490
5,514,378 A	5/1996	Mikos et al.	424/425

**FOREIGN PATENT DOCUMENTS**

EP 0747068 12/1996

**OTHER PUBLICATIONS**

“Porosity and Specific Surface of Bone” by Martin RB in CRC Critical Reviews in Biomedical Engineering, 10(3), 179–22, 1984.

K. Whang et al., “A Novel Method to Fabricate Bioabsorbable Scaffolds”, *Polymer*, Vol. 36, No. 4, pp. 837–842, 1995 Elsevier Science Ltd.

Mooney et al., “Novel Approach to Fabricate Porous Sponges of Poly (D,L–Lactic–co–glycolic acid) Without the Use of Organic Solvents”, *Biomaterials*, vol. 17, pp. 1417–1422, 1996 Elsevier Science Ltd.

Thomson et al., “Fabrication of Biodegradable Polymer Scaffolds to Engineer Trabecular Bone”, *J. Biomater. Sci. Polymer Edn.*, Vol. 7, No. 1, pp. 23–38, 1995 VSP.

Mikos et al., “Laminated Three–Dimensional Biodegradable Foams for Use in Tissue Engineering”, *Biomaterials*, Vol. 14, No. 5, pp. 323–330, 1993 Butterworth–Heinemann Ltd.

Schugens et al., “Polylactide Macroporous Biodegradable Implants for Cell Transplantation. II. Preparation of Polylactide Foams by Liquid–Liquid Phase Separation”, *Journal of Biomedical Materials Research*, Vol. 30, pp. 449–461, 1996 John Wiley & Sons.

Ishaug–Riley et al., “Three–Dimensional Culture of Rat Calvarial Osteoblasts in Porous Biodegradable Polymers”, *Biomaterials*, Vol. 19, pp. 1405–1412, 1998 Elsevier Science Ltd.

Ishaug et al., “Bone Formation by Three–Dimensional Stromal Osteoblast Culture in Biodegradable Polymer Scaffolds”, *Journal of Biomedical Materials Research*, vol. 36, pp. 17–28, 1997 John Wiley & Sons, Inc.

\* cited by examiner

*Primary Examiner*—David M. Naff

(74) *Attorney, Agent, or Firm*—Lynn C. Schumacher; Hill & Schumacher

(57) **ABSTRACT**

A polymer scaffold is provided having an extensively interconnected macroporous network with macropores having microporous struts as walls. Macropore diameter ranges from about 0.5 to about 3.5 mm. The polymer may be a biocompatible, biodegradable polymer such as poly(lactide-co-glycolide) containing 75% polylactide and 25% polyglycolide. The polymer scaffold is prepared by mixing a liquid polymer with particles, precipitating the liquid polymer with a non-solvent for the liquid polymer and dissolving the particles with a solvent to form the macroporous polymer scaffold which preferably has porosity greater than 50%. The surface of the polymer scaffold may be modified by acid or base treatment, or by collagen or calcium phosphate deposition. The polymer scaffold has utility for tissue engineering, particularly as a scaffold for in vitro and in vivo cell growth.

**16 Claims, 15 Drawing Sheets**